

Buntsteinputz

Ready-to-use decorative wall coating for highly durable interior and exterior surfaces.

Material Properties Highly permeable to water vapor, water-repellent and low stress.

Substrate As a finishing coat on substrates made of

- concrete
- Lime and lime-cement plasters of categories CSII, CS III and CS IV (previously MG P II and P III)
- Mineral reinforcement or filler plaster layers for the renovation of plaster facades
- Reinforcement layers of external thermal insulation composite systems

All substrates must be dry, sound, clean and free of adhesion-reducing residues.

Consumption - ca. 4,0 - 6,0 kg/m²

Technical Data

- **Classification** // Exterior render according to EN 15824 with organic binders
- **Density** // ca. 1,8 kg/dm³
- **Tensile strength** // >= 0,3 MPas according to EN 1542
- **Water vapour permeability S_a** // class V1 (high) according to EN ISO 7783-2
- **Water absorption** // class W2 (mid) according to EN 1062-3

| | | |
|---|--|---|
| CE | DIN EN 15824 Plaster with organic binders for exterior use | Durability (frost resistance) NPD |
| 11 | Water vapour permeability V1 high | Thermal conductivity λ 10dry, mat NPD |
| huma farben GmbH D-73563 Mögglingen | Water absorption W2 mid | Reaction to fire B-s1, d0 |
| | Tensile strength >= 0,3 N/mm ² | Product Coloured stone plaster |

Application Material is ready for use after brief stirring with a slow-speed agitator. If necessary, adjust consistency with a little water. Apply plaster to grain thickness with a stainless-steel trowel or spraying device and texture with a plastic trowel. Rougher textures are achieved when using wooden or polystyrene boards.

Clean tools with water immediately after use. To avoid build-up and structural defects, work quickly wet-on-wet and use sufficient labour for larger areas. On contiguous surfaces, only use material with the same batch number or mix materials with different batch numbers beforehand. Carefully cover neighbouring areas. Wash off splashes immediately with plenty of water. Do not use at air and building structure temperatures below +5°C, as well as in direct sunlight, draughts or expected night frosts.

Attention should be paid to
VOB, Part C, DIN 18363, Sections 2 and 3, as well as the BFS data sheets for the relevant work areas.

Façade plasters

Buntsteinputz

Application



Surface Coating

As a rule, no further coating is required. If required, the render can be overpainted with façade paint once it has dried.

Packaging

- 25 kg/pail
- 24 pails/pallet

Storage

Store the pail tightly closed in a cool and frost-free place.

Please note

Protect eyes and skin.

Giscode BSW20

Advisory service

The information in this data sheet only represents general guidelines. If you have any technical questions regarding a specific application, please contact our sales office.

Visual Appearance

Natural stone plaster

Colours

Colour assortment according to sample card

Options

All information in this publication is based on experience, tests and trials. A guarantee for the general validity of individual data and statements is excluded with regard to different processing and construction site conditions. The generally recognised and technical rules of construction technology as well as the applicable standards and guidelines must be observed. The publication of this publication renders previous editions invalid. We reserve the right to make changes in the context of further product and application technology developments. Please refer to our Internet pages for the latest information. Our current terms and conditions of sale and delivery apply to all business transactions.

Safety data sheet available on request.

huma farben GmbH
Ziegelfeldstraße 66
D-73563 Mögglingen
T +49 7174 898990

F +49 7174 8989918
www.huma-farben.de
info@huma-farben.de