


Primer

BetonPrimer W

Bonding course for gypsum plasters as well as lime and lime-cement plasters

Material Properties	Adhesion-promoting, absorbency-regulating, highly alkali- and saponification-resistant, quick-drying.
Substrate	<p>Primer to promote adhesion and reduce the absorbency of the substrate.</p> <ul style="list-style-type: none"> To avoid differences in colour, a homogeneous substrate must be created with regard to material and drying. Not suitable for horizontal surfaces. Do not apply to damp or dirty surfaces.
Consumption	ca. 0,25–0,3 kg/m ² per coat
Technical Data	<ul style="list-style-type: none"> Type // fine-rough primer Consistency // liquid Binder // Polymer dispersion, siloxane-reinforced Density // ca. 1,4 g/cm³
Application	<p>Stir thoroughly with a slow-speed agitator. Sandy and highly absorbent substrates must be stabilised with Tiefgrund LF. Apply with a roller or brush.</p> <p>Clean tools with water immediately after use. Carefully cover neighbouring surfaces. Wash off splashes immediately with plenty of water. Do not use at air and building structure temperatures below +5°C or in direct sunlight, draughts or expected night frosts.</p> 
Surface procurement	After sufficient drying (at least 24 hours at 20°C), coat with mineral or pasty finishing plasters, lime and lime/cement-based plasters and plasters containing gypsum..
Packaging	<ul style="list-style-type: none"> 20 kg/pail 24 pails/pallet
Storage	Store the pail tightly closed in a cool and frost-free place.

Primer

BetonPrimer W

Please note

Protect eyes and skin.
Giscode BSW20

Visibly wet, damp concrete surfaces or concrete with more than 3% moisture by mass must not be plastered.

Advisory service

The information in this data sheet only represents general guidelines. If you have any technical questions regarding a specific application, please contact our sales office.

Visual Appearance

Fine-rough

Colours

white

Options

All information in this publication is based on experience, tests and trials. A guarantee for the general validity of individual data and statements is excluded with regard to different processing and construction site conditions. The generally recognised and technical rules of construction technology as well as the applicable standards and guidelines must be observed. The publication of this publication renders previous editions invalid. We reserve the right to make changes in the context of further product and application technology developments. Please refer to our Internet pages for the latest information. Our current terms and conditions of sale and delivery apply to all business transactions.

Safety data sheet available on request.

huma farben GmbH
Ziegelfeldstraße 66
D-73563 Mögglingen
T +49 7174 898990

F +49 7174 8989918
www.huma-farben.de
info@huma-farben.de